## **PRODUCT**

# **Cabinent Coat Interior Satin Finish**

#### **DESCRIPTION**

A urethane fortified high performance coating made for cabinets, doors and trim with an ultra smooth factory-like finish.

### **COLORS**

- P- Pastel Base
- T- Tint Base
- D- Deep Base
- N- Neutral Base

#### **APPLICATION**

Do not apply over a surface that has not been thoroughly prepared. Stir thoroughly before and during use. Intermix all containers for color uniformity. Use a premium nylon/polyester brush or 3/8" nap roller cover. Sand entire cabinet with fine grit sandpaper. Remove all sanding dust. For best performance; apply 2-3 thin coats. To avoid drip marks or sagging do not apply too thickly.

### RECOMMENDED USES

Bare, previously painted or stained properly prepared interior cabinets, doors or trim.

# **ENVIRONMENTAL VARIABLES**

DO NOT THIN. Dries to the touch in 1-2 hours at 77° and 50% humidity. Recoat after 2 hours. High humidity or low temperature may increase dry time. After 2-4 weeks, cured paint may be cleaned with a mild, non-abrasive liquid detergent. Darker colors may require additional dry time between coats. Dry Paint film is mildew resistant. Average coverage 250-400 sq.ft. per gallon depending on the porosity of the surface to be painted.

### CLEAN-UP

Wash tools with warm water and soap immediately after applying. Properly Dispose of all soiled rags.

### **CAUTIONS**

Protect unused product from freezing.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES	
Resin Type	Urethane Fortified Acrylic
Dry Time at 60º	25-35
Weight per gallon	10.5 lbs/gal
Percent solids by weight	48.7 %
Percent solids by volume	35.26 %
Viscosity Range	102-112 KU
VOC	Less than 50 gm/L 0.42 lbs/gal

Revised: 04/2023

## Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.