

PRODUCT

Interior/Exterior Gloss Polyurethane Floor

DESCRIPTION

An extremely durable oil based porch and floor coating resists abrasion, scuffing, chipping and cracking.

COLORS

White	DP-1	Tint Base	DP-T
Black	DP-2	Deep Base	DP-D
Light Gray	DP-3	Neutral Base	DP-N
Tile Red	DP-4		
Medium Gray	DP-5		
Dark Gray	DP-10		
Rich Brown	DP-13		
Hunter Green	DP-15		

SURFACE PREP

Remove dirt, dust, grease and oil residue, loose and peeling paint or rust. Glossy areas must be dulled by sanding. Spot coat worn or bare areas. Allow new concrete to age 90 days before painting. Acid etch all bare concrete to the roughness of 100 grit sandpaper (this may require several etchings) before painting.

APPLICATION

Stir or mix paint before using and intermix all containers for color uniformity. The dried film will become slippery when wet. The addition of a non-slip agent such as silica sand is recommended prior to application. Apply as-is with brush, roller or pad painter. For spraying information contact your paint specialist. Do not overspread. Surface temperature must be above 40°F (5°C).

RECOMMENDED USES

Covered exterior wood, interior wood, and interior concrete. Use on porches, basement floors, utility rooms and other surfaces on which a wear-resistant coating is needed.

ENVIRONMENTAL VARIABLES

DO NOT THIN. Dries overnight. Low temperature or high humidity may increase dry time. On garage floors allow paint to dry 48 hours before driving on paint. Shield areas under tires for first 2 weeks with corrugated cardboard. Coverage of 450 sq. ft. per gallon .

CLEAN-UP

Use mineral spirits (paint thinner) to clean up. Properly Dispose of all soiled rags.

CAUTIONS

Do not expose this container to excessive heat. Close container after each use. Keep from freezing.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES

Resin Type	Alkyd/Polyurethane
Dry Time at 60°	6 +
Weight per gallon	9.42
Percent solids by weight	67.0 %
Percent solids by volume	52.0 %
Viscosity Range	77-82 KU
VOC	Less than 375 g/L

Revised: 04/2023

General Paint Manufacturing
201 Jandus Road • Cary, Illinois 60013
Phone: (800) 323-7545
www.truevaluepaint.com

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.