

PRODUCT

Interior/Exterior Urethane Fortified Semi-Gloss Porch & Floor Coating

DESCRIPTION

A low VOC, urethane fortified, ultra durable porch and floor coating with exceptional durability and a mildew resistant finish.

COLORS

White	USGF-1	Tint Base	USGF-T
Light Gray	USGF-3	Deep Base	USGF-D
Tile Red	USGF-4	Neutral Base	USGF-N
Medium Gray	USGF-5		
Dark Gray	USGF-10		

SURFACE PREP

Remove dirt, dust, grease and oil residue, loose and peeling paint or rust. Glossy areas must be dulled by sanding. Spot coat worn or bare areas. Allow new concrete to age 90 days before painting. Acid etch all bare concrete to the roughness of 100 grit sandpaper (this may require several etchings) before painting.

APPLICATION

Stir or mix paint before using and intermix all containers for color uniformity. Apply as is with brush, roller, pad painter or spray. On new concrete apply 2 coats, thinning first coat with ½ pt. of water per gallon. Prime all bare metal with proper metal primer. On bare wood apply 2-3 coats of this products. Surface temperature must be above 50°F (10°C). To reduce slipperiness, silica sand may be added.

RECOMMENDED USES

Covered exterior wood, interior wood, and interior concrete. Use on porches, basement floors, utility rooms and other surfaces on which a wear-resistant coating is needed.

ENVIRONMENTAL VARIABLES

Thin sparingly with water if necessary for spraying. Dries to the touch in 2-8 hours. Recoat if necessary after 24 hours. High humidity or low temperature may increase dry time. After 2-4 weeks, cured paint may be cleaned with a mild, non-abrasive liquid detergent. Dry paint film is mildew resistant. Coverage of 250-450 sq. ft. per gallon depending on the porosity of the surface to be painted.

CLEAN-UP

Wash tools with warm water and soap immediately after applying. Properly Dispose of all soiled rags.

CAUTIONS

Do not expose this container to excessive heat. Close container after each use. Keep from freezing.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES

Resin Type	Acrylic/Polyurethane
Dry Time at 60°	40-50
Weight per gallon	10.4 lbs./gal
Percent solids by weight	43.3 %
Percent solids by volume	28.5 %
Viscosity Range	85-95 KU
VOC	Less than 100 g/L

Revised: 04/2023

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.