

PRODUCT

Interior Water-Based Vapor Barrier Primer PRP-1

DESCRIPTION

This product is specially formulated to reduce moisture vapor transmission through the walls of your home. By maintaining humidity in your home during the winter, your home will be more comfortable. Designed for use on all interior walls made of drywall or plaster.

COLORS

White PRP-1

SURFACE PREP

Remove loose paint, wash off dirt and grease with detergent. Allow to thoroughly dry. Scuff-sand and dull glossy surfaces. Patch cracks and spot prime with this product.

APPLICATION

Stir thoroughly before and during use. Do not apply over a surface that has not been properly prepared. Use product when surface and air temperature are between 50°F – 90°F. Do not over spread. Use a high quality 3/8 inch nap roller cover or nylon/polyester brush. If applying by roller, roll from dry area into the wet using firm crisscrossing strokes. Finish with long ceiling to floor strokes in one direction. Paint the ceiling first, then the walls. Allow new masonry to cure at least 30 days before coating.

RECOMMENDED USES

All interior walls and ceiling surfaces such as drywall, plaster, wood, stone & concrete. Ideal for use over drywall mud and tape joint compound. This product meets moisture vapor barrier specification when tested under ASTM D-1653-91A and ASTM E-96.

ENVIRONMENTAL VARIABLES

DO NOT THIN. Dries in 1 hour. Recoat in 4 hours. Low temperature or high humidity may increase dry time. Average coverage 400 sq. ft. per gallon.

CLEAN-UP

Tools, drips and spills should be cleaned with soap and warm water immediately. Properly dispose of all soiled rags.

CAUTIONS

Protect unused product from freezing.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES

Resin Type	Styrene Butadiene Latex
Dry Time at 60°	1-4
Weight per gallon	10.56 lbs. $\pm 2\%$
Percent solids by weight	41.0 % $\pm 2\%$
Percent solids by volume	27.0 % $\pm 2\%$
Viscosity Range	84-88 KU
VOC	Less than 200 g/L

Revised: 04/2023

General Paint Manufacturing
201 Jandus Road • Cary, Illinois 60013
Phone: (800) 323-7545
www.truevaluepaint.com

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.