

PRODUCT

Premium Décor High Heat

DESCRIPTION

Superior interior/exterior high heat enamel spray at any angle, comfort spray tip. Takes heat up to 1000°F.

COLORS

Aluminum	PDS-1550
Flat White	PDS-1551
Flat Black	PDS-1552

SURFACE PREP

Remove all grease, oil, dirt, wax and rust scale from surface. On new clean surface no primer is necessary. For rusty metal surfaces prime with X-O Rust Primer. New galvanized surfaces must weather 6 months before priming. Use with adequate ventilation.

APPLICATION

Before spraying, shake can for 2 minutes after ball within begins to rattle and occasionally during use. Hold can 10" to 18" (25 to 45 cm) away from the surface and apply several thin coats a few minutes apart rather than one heavy coat, slightly overlapping each stroke. Keep can in motion while spraying. Recoat within one hour.

RECOMMENDED USES

For interior or exterior surfaces such as barbecues, car engines, boilers, heaters, steam pipes and furnaces. Will not with-stand open flame. Do not use on Styrofoam, ceramic tiles or marble.

ENVIRONMENTAL VARIABLES

Flat White & Black: Set to touch in 20-50 minutes. Tack free in 3-4 hours. Aluminum set to touch in 5-10 minutes. Tack free in 10-30 minutes. Recoat within one hour. High humidity or low temperature may increase dry time. Contains no CFC's which deplete the ozone layer

CLEAN-UP

Never stick sharp objects into the opening at the top of the can. For wet film, use mineral spirits. For dry film, use paint stripper, toluol or acetone.

CAUTIONS

Contains propane, acetone and aromatic solvents. Extremely flammable. Storage and handling: Level-3 Aerosols. Do not use on Styrofoam, ceramic tiles or marble. Do not store at temperatures above 120°F (50°C). Protect unused product from freezing.

Dispose of aerosol container and unused contents in accordance with local, state and federal regulations. Do not burn, incinerate, puncture or place aerosol container in home garbage compactor. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES

VOCs	Max 80% & 1.85 pw MIR
Flashpoint	< 20° F
Percent solids by weight	22.40% + - 2 PDS 1550
Dry Time at 60°	White & Flat Black: 0-10

Revised: 04/2023

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.