

## PRODUCT

### Premium Décor Lacquer

## DESCRIPTION

Superior interior/exterior decorative lacquer enamel spray at any angle, comfort spray tip. Great for use on wood, metal and furniture. Easy to sand.

## COLORS

Black	PDS-1353
White	PDS-1354
Clear	PDS-1355

## SURFACE PREP

Remove all grease, oil, dirt, wax and rust scale from surface. On new clean surface no primer is necessary. For rusty metal surfaces prime with X-O Rust Primer. New galvanized surfaces must weather 6 months before priming. Use with adequate ventilation.

## APPLICATION

Before spraying, shake can for 2 minutes after ball within begins to rattle and occasionally during use. Hold can 10" to 18" (25 to 45 cm) away from the surface and apply several thin coats a few minutes apart rather than one heavy coat, slightly overlapping each stroke. Keep can in motion while spraying. Recoat within one hour.

## RECOMMENDED USES

For wood, metal, furniture, tools, handcrafts and other paintable surfaces. Do not use on Styrofoam, ceramic tiles or marble.

## ENVIRONMENTAL VARIABLES

Set to touch in 5-20 minutes. Tack free in 15-45 minutes. Recoat anytime. High humidity or low temperature may increase dry time. Contains no CFC's which deplete the ozone layer

## CLEAN-UP

Never stick sharp objects into the opening at the top of the can. For wet film, use mineral spirits. For dry film, use paint stripper, toluol or acetone.

## CAUTIONS

Contains propane, acetone and aromatic solvents. Extremely flammable. Storage and handling: Level-3 Aerosols. Do not use on Styrofoam, ceramic tiles or marble. Do not store at temperatures above 120°F (50°C). Protect unused product from freezing.

Dispose of aerosol container and unused contents in accordance with local, state and federal regulations. Do not burn, incinerate, puncture or place aerosol container in home garbage compactor. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

## PHYSICAL PROPERTIES

VOC – Black & White	Max 65% & 0.95 pw MIR for PD1353 & PD1354
VOC – Clear	Max 67% & 0.85 pw MIR for PD1355
Flashpoint	< 20° F
Percent solids by weight	15.45% + - 2
Dry Time at 60°	80 Minutes

Revised: 04/2023

### Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.