

**PRODUCT**

**Water Based Polyurethane  
 Wood Varnishes**

**RECOMMENDED USES**

Exterior Floor, Gym Floor, Furniture, trim, paneling, doors, cabinets and woodwork.

**FINISHES**

Satin WSV10  
 Semi-Gloss WSV30

**APPLICATION**

Do not apply over a surface that has not been thoroughly and properly prepared. Stir thoroughly before use, **DO NOT SHAKE**. Use quality natural brush or pad applicator. When applying over unvarnished wood, use fine grade sandpaper then wipe clean with a tack cloth. Apply one or more coats to achieve the desired appearance. **DO NOT USE STEEL WOOL**. For application over previously varnished surfaces that have been properly prepared apply one or two coats. Allow to dry between coats. Sand lightly with sandpaper and wipe with tack cloth between coats. **DO NOT** apply over lacquer or shellac. Always maintain a wet edge to avoid lap marks. Be sure to allow adequate dry time between coats.

**LIMITATIONS**

Do not use over non-wood surfaces. Do not expose this product to excessive heat. Close container after each use. Do not thin.

**ENVIRONMENTAL VARIABLES**

Dry times at 70-80F and 50% humidity are set to touch in 15-30 minutes and tack free in 1 - 2 hours. Recoat after 2 hours. Coverage of 300-400 Sq. FT / Gallon

**SIZES**

Quart, Gallon

**CLEAN-UP**

Wash tools with soap and water immediately after applying.

**CAUTIONS**

Protect unused product from freezing.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

**PHYSICAL PROPERTIES**

Dry Time at 60°	80-100
Dry Film Thickness	1.0 – 2.0 mils
Wet Film Thickness	2.5 to 5.0 mils
Viscosity Range	50 – 65 KU
VOC	275 g/L

Revised: 05/2023

**Limited Warranty**

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.