

PRODUCT

X-O Interior/Exterior Acrylic Direct to Metal Enamel

DESCRIPTION

Interior/Exterior 100% Acrylic Direct to Metal Rust Preventative Enamel dries quickly with low odor. Superior rust protection resists abrasion, weathering and fading.

COLORS

Gloss White WXO -1

SURFACE PREP

Remove dirt, dust, chalk, grease, loose paint or rust. Heavily rusted areas should be scraped or wire brushed to a sound surface. Dull glossy areas with sandpaper. Rinse area with mineral spirits to remove any oil or grease. Allow surface to dry before priming.

APPLICATION

Stir thoroughly before and during use. Apply as is with a good quality brush, roller or paint pad. Do not overspread. Surface temperature must be above 50° F (10° C). Do not apply in the hot sun. Do not apply if rain or dew is expected. May also be sprayed.

RECOMMENDED USES

Interior or exterior metal surfaces, such as file cabinets, fencing, metal drains, piping, and tools. Ideal for metal roofs.

ENVIRONMENTAL VARIABLES

DO NOT THIN. Usually dries in 2-4 hours. Low temperature or high humidity may increase dry time. Coverage of 400-450 sq. ft. per gallon.

CLEAN-UP

Clean up with soap and water.

CAUTIONS

Do not expose this container to excessive heat. Close container after each use.

Disposal - Full: Give remaining product to neighbors or community organization. Partially full: (If state or local regulations allow) Pour residue into absorbent material. When dry, dispose of in trash for pick up. Empty: This container may be accepted in a recycling program. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

PHYSICAL PROPERTIES

Resin Type	Acrylic Polymer
Dry Time at 60°	60 +
Weight per gallon	10.0 lbs.
Percent solids by weight	48.3 %
Percent solids by volume	36.5 %
Viscosity Range	95-105 KU
VOC	Less than 50 g/L

Revised: 05/2023

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since GPM does not control the application of its products, or the condition of the surfaces to which they are applied, GPM's liability will under no circumstances exceed replacement of the product.