EASYCARE

365 Paint & Primer In One Exterior Flat Finish

DESCRIPTION

A durable 100% acrylic latex flat house paint with a 15 year warranty when applied according to all label directions on a properly prepared surface.

EXF FORMULA ANALYSIS

Resin Type: Acrylic Latex

Sheen/Type Finish:

1-4 @60° / Flat

Weight per Gallon = 11.2 lbs. + .2

Percent Solids by Weight = 47.1 % + 2%

Percent Solids by volume = 30.5% + 2%

Viscosity Range = 95-105

V.O.C. = Less than 50 g/L

Coverage= 350-400 sq., ft., per gallon.



PRODUCT FEATURES

- Fade resistant
- •Washable
- Easy soap & water clean-up

BASES AVAILABLE

EXF-P Pastel Base

EXF-T Tint Base

EXF-Neutral Base

RECOMMENDED USE

Previously painted or primed exterior surfaces including concrete, masonry, vinyl, aluminum and factory primed siding.

THINNING: Thin sparingly with water if necessary for spraying.

DRY TIME: Dries to the touch in 1-2 hours. Recoat if necessary after 4 hours. High humidity or low temperature may increase dry time. After 2-4 weeks, cured paint may be cleaned with a mild, non-abrasive liquid detergent. Dry paint film is mildew resistant.

COVERAGE: 350-400 sq.. ft.. per gallon depending on the porosity of the surface to be painted. **CLEAN UP & DISPOSAL:** Wash tools with warm water and soap immediately after applying. Properly Dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only)

STORAGE: Protect unused product from freezing.

APPLICATION METHOD

This paint can be used over latex or oil based paint. Intermix all containers for color uniformity. Stir thoroughly before and during use. Certain colors may require more than one coat. Do not apply over a surface that has not been properly prepared. Do not apply if rain or dew is expected within 24 hrs or if outside temperature could drop below 40°. Use product when surface and air temperature are between 50-90°. Do not apply in hot sun; follow shade around house. Do not over spread. Use a premium brush or pad applicator. If spray applied back brushing is recommended to assure adequate penetration into the substrate . For best performance; apply two coats on new surfaces after priming. Allow new masonry to cure at least 30 days before coating

SURFACE PREP

See "Surface Prep" section for recommendations