

# EASYCARE

## Interior/Exterior Urethane Fortified Satin Porch & Floor Coating

### DESCRIPTION

A low VOC, urethane fortified, ultra durable porch and floor coating with exceptional durability and a mildew resistant finish.

#### • USF FORMULA ANALYSIS

- Resin Type: Acrylic / Polyurethane Dispersion Sheen/Type Finish:
- 25-35 @60° / Satin
- Weight per Gallon = 10.3 lbs. /gal
- Percent Solids by Weight = 43.1 %
- Percent Solids by volume = 28.5 %
- Viscosity Range = 85-95 KU
- V.O.C. = Less than 100 g/L
- Coverage: 250-450 sq. ft. per gallon

### RECOMMENDED USE

Covered exterior wood, interior wood, and interior concrete. Use on porches, basement floors, utility rooms and other surfaces on which a wear-resistant coating is needed.

**THINNING:** Thin sparingly with water if necessary for spraying.

**DRY TIME:** 77° @ 50% humidity: Dries to the touch in 2-8 hours. Recoat if necessary after 24 hours. High humidity or low temperature may increase dry time. After 2-4 weeks, cured paint may be cleaned with a mild, non-abrasive liquid detergent. Dry paint film is mildew resistant.

**COVERAGE:** 250-450 sq. ft. per gallon depending on the porosity of the surface to be painted.

**CLEAN UP:** Wash tools with warm water and soap immediately after applying.

Properly dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

**STORAGE:** Protect unused product from freezing.

### APPLICATION METHOD

Stir or mix paint before using and intermix all containers for color uniformity.

Apply as is with brush, roller, pad painter or spray.

On new concrete apply 2 coats, thinning first coat with ½ pt. of water per gallon.

Prime all bare metal with proper metal primer. On bare wood apply 2-3 coats of this products.

Surface temperature must be above 50°F (10°C). To reduce slipperiness, silica sand may be added.

### SURFACE PREP

Remove dirt, dust, grease and oil residue, loose and peeling paint or rust.

- Glossy areas must be dulled by sanding.
- Spot coat worn or bare areas.
- Allow new concrete to age 90 days before painting.
- Acid etch all bare concrete to the roughness of 100 grit sandpaper (this may require several etchings) before painting.



### PRODUCT FEATURES

- High Hiding Formula
- Superior Fade Resistance
- Stain Resistant
- Washable
- Low Odor, Low VOC

### COLORS & TINTING

- |                   |                    |
|-------------------|--------------------|
| USF-1 White       | USF-T Tint Base    |
| USF-3 Light Gray  | USF-D Deep Base    |
| USF-4 Tile Red    | USF-N Neutral Base |
| USF-5 Medium Gray |                    |
| USF-10 Dark Gray  |                    |