

TruStripe Fast Dry Exterior Latex Zone Marking Paint



DESCRIPTION

Exterior Latex Fast Dry Zone Marking paint ideal for marking curbs, parking lots, factory floors and warehouses. For best results apply with automatic marking equipment.

Formula Analysis

- Resin Type-Acrylic Latex
- Sheen/Type Finish:
- 0-9 @60° / Flat
- Weight per Gallon = 14.7 ± 0.5 lbs.
- Percent Solids by Weight = 73.1% ± 2%
- Percent Solids by volume = 59.2% ± 2%
- Viscosity Range = 80-90 KU
- V.O.C. = Less than 50 g/L

PRODUCT FEATURES

- Dries Quickly- 14 minutes
- Durable
- Weather and fade resistant
- Flexible
- Good Gloss bead adhesion
- Meets Federal Color Standards

COLORS

- 1033 White
- 1034 Yellow
- 1035 Black
- 1036 Red
- 1037 Blue
- 1038 Green

RECOMMENDED USE

For marking curbs and safety zones on streets and parking lots. May also be used for marking playgrounds, tennis courts, safety and storage areas in factories and warehouses.

THINNING: Thin only if necessary; using water and not exceeding 1 pint per gallon.

DRY TIME: Dries to the touch in 14 minutes. Sets up in 10 to 20 minutes. High humidity or low temperature may increase dry time.

CLEAN UP: Wash tools with warm water and soap immediately after applying followed by mineral spirits if using striping equipment.

Properly dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

STORAGE: Protect unused product from freezing.

COVERAGE:

<u>Width of line</u>	<u>Linear feet per gallon</u>
3" (76.2mm)	600 feet (187 meters)
4" (101.6 mm)	450 feet (137 meters)
5" (127 mm)	350 feet (110 meters)
6" (152.4 mm)	300 feet (91 meters)

Coverage is based on applying the average wet film at 13 mils 125 sq. ft. per gallon.

APPLICATION METHOD

- Stir paint before and during use. Apply with brush, marking roller or line striping equipment.
- No thinning is necessary (see paint specialist for details). Avoid marking if surface temperature is below 50°F (5°C) or rain is expected.

SURFACE PREP

- Clean surface to remove dirt, grease, oil and loose and peeling paint.
- When applied over emulsified coal tar compounds and sealers the surface must first age 7 days.