



X-O Rust Interior/Exterior Oil Base Farm & Implement Enamel

DESCRIPTION

Direct to metal rust preventative enamel for interior and exterior metal surfaces such as tractors, trucks, machinery and farm equipment.

COLORS

XO FORMULA ANALYSIS

Resin Type-Long and Medium OIL

Alkyd/Soya Alkyd

Sheen/Type Finish:

60 + at 60°/Gloss

Weight per Gallon = 9.20 pounds

Percent Solids by Weight = 64.0 %

Percent Solids by Volume = 49.0 %

Viscosity = 80-90 KU

V.O.C. = Less than 400g/L.

Coverage=400-450 sq. ft. per gallon

MPI# 48

Product Features

- Excellent color retention
- Weather resistant
- Prevents rust
- For metal substrates only

Colors

XO -34 Ford Blue

XO -35 Int. Harvester Red

XO -36 John Deere Green

XO -37 John Deere Yellow

XO -38 Caterpillar Yellow

RECOMMENDED USE: Interior or exterior metal surfaces, such as tractors, trucks, machinery, fencing, farm equipment and tools. **Not recommended for roofs.**

THINNING: DO NOT THIN.

DRY TIME: Usually dries in 8 hours. Low temperature or high humidity may increase dry time.

CLEAN UP: Use mineral spirits (paint thinner). Properly dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only).

STORAGE: Do not expose this container to excessive heat. Close container after each use.

APPLICATION: Stir or mix paint before and during use. For color uniformity intermix all containers. Apply with brush, roller or paint pad. Do not thin. Do not overspread. When painting with a color that was tinted by the store, always prime before painting. Surface temperature must be above 40°F (5°C). Average coverage 450 sq. ft. per gallon.

SURFACE PREP:

- Remove dirt, dust, chalk, grease, loose paint or rust.
- Heavily rusted areas should be scraped or wire brushed to a sound surface.
- Dull glossy areas with sandpaper.
- Rinse area with mineral spirits followed by soap and water to remove any oil or grease. Rinse thoroughly.
- Allow surface to dry before priming.