

EASYCARE

Tru-Seal Clear Multi-Surface Waterproofing Sealer – CS-1



DESCRIPTION

Penetrates and protects wood, masonry and concrete

CS-1 FORMULA ANALYSIS

Sheen/Type Finish Clear

Weight per Gallon 6.68 pounds

Percent Solids by Weight 25.13%

Percent Solids by Volume 21.83%

Viscosity 6"-12" Ford Cup

V.O.C. Less than 600 g/L

PRODUCT FEATURES

Formulated to protect against moisture damage to: Brick, Patios, Hardboard, Wood, Masonry, Concrete and other porous surfaces

RECOMMENDED USE

Protects wood, concrete, masonry, brick, composition surfaces, and other porous surfaces.

DRY TIME: 24-48 hours for a single coat. If a second coat is needed, allow 48 hours before application.

CLEAN UP: Clean up tools, drips and spills immediately with mineral spirits (paint thinner).

DISPOSAL: Properly Dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only) or visit www.Earth911.org.

LIMITATIONS: Do not apply paint, stain or varnish over Tru-Seal, or use as an additive to any coating. Do not apply over rubber, plastic, asphalt, canvas or sealed surfaces.

APPLICATION METHOD

Apply by brush, roller, dip or spray without thinning. A garden sprayer is suitable for spraying. Apply liberally in a uniform manner. If too much is applied, a non-drying residue will form. This may be removed by wiping with a rag. Test for compatibility prior to application. Average coverage is 100 to 200 sq. ft (9 to 19 square meters) per gallon (3.78L) depending on surface porosity.

DO NOT APPLY OVER PAINT, RECENTLY STAINED SURFACES, VARNISH, RUBBER, PLASTIC, ASPHALT OR SEALED SURFACES. DO NOT USE AS AN ADDITIVE. DO NOT BLEND OR MIX WITH OTHER TRU-SEAL WATER-PROOFING PRODUCTS.

SURFACE PREP

All surfaces must be clean, dry and porous. Surface is suitable for application if a small amount of water can be quickly absorbed.